



SEALOCRETE PLA LTD Greenfield Lane
Rochdale OL11 2LD Tel: 01706 352255, Fax 01706 860880



TECHNICAL DATA SHEET TDS077
PUBLISHED JANUARY 2003

LIQUID GLOSS PAINT

DESCRIPTION

A high opacity liquid gloss paint, suitable for use on primed and prepared wood, metal and masonry surfaces.

PROPERTIES

Based on a high quality long oil modified system SEALOCRETE LIQUID GLOSS PAINT has been formulated to impart excellent obliteration combined with a hard durable gloss finish.

MAIN USES

Particularly suitable for application where an aesthetic but durable finish is required. Designed for most household applications inside and out, eg. windows, doors skirting boards etc. SEALOCRETE LIQUID GLOSS has many varied uses on a variety of substrates when used in conjunction with Sealocrete Undercoat.

BENEFITS

- * Hardwearing and durable.
- * Easy to use
- * Contains no added lead.
- * High opacity.
- * For interior and exterior use.

RECOMMENDED SYSTEM

After suitable surface preparation and priming of substrate, one coat of Sealocrete Undercoat followed by one or two coats of Sealocrete Liquid Gloss as desired.

COLOURS:

Brilliant White, Magnolia, Black

PACKAGING:

750ml, 2.5 litres, 5 litres.

TECHNICAL INFORMATION

Drying Times: Surface Hard Dry:	2-4 hours 16 Hours
Recoatable	Overnight
Coverage	Up to 70m per 5 litre depending on substrate porosity.
Flash point:	32°C

CLEANING

Clean all equipment immediately with White Spirit.

Do not apply in cold or damp conditions. Store away from flames and sources of ignition.

Stir well before use.

SURFACE PREPARATION

All surfaces must be clean, dry and free from grease, oil, waxes etc. Loose and flaking material should be properly removed.

Previously decorated surfaces should be adequately rubbed down and one coat of Sealocrete Undercoat applied followed by one coat of SEALOCRETE LIQUID GLOSS.

APPLICATION

Application can be by brush, roller or airless spray.

Brush: Thinning not normally required

Roller: Thinning not normally required.
Roller should be short pile variety.

Conventional spray: Thin up to 5% if desired with White Spirit.

Airless spray: Dependent upon equipment and application conditions, thinning may not be required but up to 10% thinner may be used if desired.

Spray tip: 11-13 thou (0.28-0.33mm)
Spray angle: 50° - 70°
Minimum pressure: 2000 psi.

HEALTH AND SAFETY

As with all paints and coatings, as long as reasonable standards and safe working are maintained then there should be no major hazards in the handling of this product.

STORAGE LIFE

Shelf life is at least 12 months when stored as directed in undamaged and unopened containers.

We endeavour to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, we have no control over the circumstances in which our product is used and it is therefore important that the end user satisfy himself by prior testing that the product is suitable for his specific application and that the actual conditions of use are suitable. Accordingly, no responsibility can be accepted, or any warranty given by ourselves, our representatives, agents or distributors, other than that the product as supplied by us will meet our written specification. Products are sold subject to our standard conditions of sale and each purchaser and end user should at all times ensure that he has consulted our latest product instructions and safety information.

