



SEALOCRETE PLA LTD Greenfield Lane
Rochdale OL11 2LD Tel: 01706 352255, Fax 01706 860880

CI/SfB

TECHNICAL DATA SHEET TDS076
PUBLISHED JANUARY 2003

SUPER PRIMER

DESCRIPTION

A specially formulated oil based primer for wood as part of an undercoat/gloss system.

PROPERTIES

SEALOCRETE SUPER PRIMER is based on a Long Oil Alkyd modified system. It provides a tough, flexible primer and will seal suitably prepared wood surfaces providing an excellent key for subsequent coats of undercoat and gloss finishes.

SEALOCRETE SUPER PRIMER contains no added lead and is suitable for both interior and exterior application.

MAIN USES

Formulated primarily for softwoods (new and old) the product can also be used on non-oily hardwoods and burnt off woodwork and most applications to suitably prepared timber prior to undercoating.

BENEFITS

- * Ease of application.
- * Interior and exterior use.
- * Excellent sealing properties.
- * Tough and flexible

TECHNICAL INFORMATION

<i>Drying Times:</i> Surface Dry Hard Dry	4 - 6 hours 16 hours
Re-coatable	Overnight
Coverage	Up to 70m ² per 5 litres depending on substrate porosity.
Flashpoint	32°C

RECOMMENDED SYSTEM

After suitable preparations and knotting of the substrate, apply one coat of SEALOCRETE SUPER PRIMER and allow to dry before following on with subsequent decorative finishes.

COLOURS

White and Pink

PACKAGING

750ml, 2.5 litre and 5 litres

SURFACE PREPARATION

All surfaces must be clean, dry and free from dirt, oil, grease, wax etc and loose and flaking material. Knots and resinous areas must be sealed using an appropriate Knotting Solution. Some hardwoods (such as Garjun, Agba and Gaboon) are very resinous and may require an Aluminium Primer. Teak, Iroku and Keruing exude an oily secretion which should be washed with White Spirit prior to painting.

APPLICATION

Application of Super Primer may be by brush, roller or airless spray.

Brush: Thinning not normally required.

Roller: Thinning not normally required.

Conventional spray: Thin up to 10% thinners if desired.

Airless spray: Depending on equipment and application conditions, thinning may not be required but up to 10% thinner may be used if desired.

Spray tip: 11 - 13 thou (0.28 - 0.33mm)

Spray angle: 50° - 60°

Minimum pressure: 2000 psi

Unprotected timber absorbs moisture and should be allowed to dry prior to painting.

STORAGE LIFE

Shelf life is at least 12 months when stored as directed in undamaged and unopened containers.

CLEANING

Clean all equipment immediately with White Spirit.

Do not apply in cold or damp conditions.

Store away from flames and sources of ignition.

Stir well before use.

HEALTH AND SAFETY

As with all paints and coatings, as long as reasonable standards and safe working are maintained then there should be no major hazards in the handling of this product.

We endeavour to ensure that any advice, recommendation or information we may give in product literature is accurate and correct. However, we have no control over the circumstances in which our product is used and it is therefore important that the end user satisfy himself by prior testing that the product is suitable for his specific application and that the actual conditions of use are suitable. Accordingly, no responsibility can be accepted, or any warranty given by ourselves, our representatives, agents or distributors, other than that the product as supplied by us will meet our written specification. Products are sold subject to our standard conditions of sale and each purchaser and end user should at all times ensure that he has consulted our latest product instructions and safety information.

